

(12) UK Patent Application (19) GB (11) 2 359 563 (13) A

(43) Date of A Publication 29.08.2001

(21) Application No 0030938.5

(22) Date of Filing 19.12.2000

(30) Priority Data

(31) 12030449

(32) 08.02.2000

(33) JP

(71) Applicant(s)

Daido Metal Company Ltd.
(Incorporated in Japan)
2 Sanage-cho, Kita-ku, Nagoya-shi, Japan

(72) Inventor(s)

Kenji Sakai
Naohisa Kawakami
Satoru Kurimoto
Koichi Yamamoto
Takayuki Shibayama

(74) Agent and/or Address for Service

fJ Cleveland
40-43 Chancery Lane, LONDON, WC2A 1JQ,
United Kingdom

(51) INT CL⁷

C22C 9/00, F16C 33/12

(52) UK CL (Edition S)

C7A AB23Y AB230 AB235 AB238 AB24X AB242 AB249
AB25Y AB250 AB26X AB261 AB263 AB265 AB267
AB269 AB27X AB271 AB273 AB275 AB277 AB279
AB289 AB309 AB319 AB32X AB32Y AB320 AB349
AB369 AB37Y AB370 AB375 AB377 AB379 AB38X
AB381 AB383 AB385 AB387 AB389 AB399 AB419
AB439 AB44Y AB440 AB449 AB45X AB451 AB453
AB455 AB46Y AB460 AB469 AB470 AB473 AB475
AB477 AB479 AB48X AB481 AB483 AB485 AB487
AB489 AB50Y AB500 AB509 AB51X AB511 AB513
AB515 AB517 AB519 AB52Y AB528 AB53X AB531
AB533 AB535 AB537 AB539 AB549 AB559 AB610
AB613 AB616 AB617 AB619 AB62X AB62Y AB621
AB624 AB627 AB630 AB633 AB635 AB66X AB661
AB663 AB665 AB666 AB667 AB669 AB670 AB675
AB682 AB684 AB686 AB688 AB70X AB702 A71X A713
A743 A744 A747 A748 A749 A757 A759 A782 A783
F2A AD44 A101 A115 A119 A150 A160 A171 A182


(56) and (58) continued overleaf

(54) Abstract Title

Copper sliding alloy

(57) A sintered copper alloy which has a Vickers Hardness of not less than 100 comprises (in mass %): 0.5-15 % Sn; one of 0.5-10 % Ni, 0.1-10 % Ag or 0.1-10 % Ni + Ag; 1-10% Pb + Bi; not more than 40 % of one or more of Fe, Al, Zn, Mn, Co and P; with the balance being copper. The alloy comprises intermetallic compounds 8 adjacent islands of a lead and/or bismuth phase 7. Also a plain bearing comprising a back metal (2, Fig. 3), a bonding layer (3, Fig. 3), a layer of the copper alloy (4, Fig. 3) and an overlay (5, Fig. 3) of resin and/or metal. The bearing can be made by spreading a pre-alloyed powder or a powder mixture of alloy components on a copper plated steel backing, sintering at 800-920°C in a reducing atmosphere, rolling and then further sintering the powder. To generate more intermetallic phase, the bearing can then be heated at 350-500°C for several hours, followed by further rolling if the sintered layer does not have a hardness of 100 VHN.

FIG. 1B



GB 2 359 563 A

(56) Documents Cited

GB 2355016 A	GB 2312679 A	GB 2285266 A
GB 0648379 A	JP 620067143 A	JP 070166278 A
US 5303817 A	US 5282908 A	US 4608085 A
US 4334926 A		

(58) Field of Search

UK CL (Edition S) F2A AD38 AD44
INT CL⁷ C22C , F16C 33/12
Online: PAJ, WPI

1/4

FIG. 1A





FIG. 1B






FIG. 2




FIG. 3

FIG. 4





FIG. 5



BACKGROUND OF THE INVENTION

5 1. Field of the invention

The present invention relates to a copper alloy sliding material and a plain bearing with the sliding material, more particularly a copper alloy sliding material having improved properties of fatigue
10 resistance and anti-seizure.

2. Brief description of the art

There has been known a plain bearing with utilization of the Kelmet as the copper alloy sliding material. The Kelmet plain bearing has been used for
15 motor vehicle engines and so on, which comprises a back steel, a sintered Cu-Pb system alloy layer provided on the back steel and an overlay layer provided on the sintered Cu-Pb system alloy layer. The Kelmet plain bearing exhibits good anti-seizure property even if the
20 overlay layer is worn out because Pb in the under layer of sintered Cu-Pb system alloy layer is supplied to the sliding-contact surface.

Thus, the known copper alloy sliding materials, typically the Kelmet bearing, have improved
25 anti-seizure property because of a much amount of Pb (i.e. about 20 mass %). While preferably the Pb amount is smaller because Pb adversely affects on the environment, if it is reduced, the anti-seizure

property is deteriorated since Pb has such an effective function as mentioned above.

On the other hand, in recent motor vehicle engines, bearings tend to be exposed to a higher temperature and a higher specific load because of high rotational speed and high power thereof. However, since the conventional Kelmet bearing contains Pb in a much amount of about 20 mass %, which is soft and has the low melting point, it has low strength and poor fatigue resistance especially under a high specific load and has a problem that Pb exposed to a high temperature flows out excessively from its initial points under the sliding-contact with the mating shaft resulting in failure of keeping good anti-seizure property.

SUMMARY OF THE INVENTION

The present invention is proposed under the above technical background.

An object of the invention is to provide a copper alloy sliding material and a plain bearing with the copper alloy sliding material, which can have excellent anti-seizure property while reducing the Pb content and further which exhibits good anti-seizure and fatigue resistance properties even under a high temperature and a high specific load.

The present inventors found that the copper alloy sliding material can have improved bearing

properties, especially anti-seizure and fatigue resistance properties by providing it with an alloy structure in which intermetallic compound grains are present adjacently to Pb phase islands and/or the Bi phase islands. Such a copper alloy sliding material exhibits excellent foreign substance embeddability and excellent anti-adhesion property since the Pb and Bi phases are soft, and has improved wear resistance since the intermetallic compound is harder than the matrix.

10 In the case where there are present hard intermetallic compound grains between the Pb and/or Bi phase islands and the matrix, the sliding material can have improved anti-seizure property, since, under load or due to wear, the surface (bearing surface) of the sliding

15 material has projections at hard intermetallic compounds grains 8 and recessions at the soft Pb and/or Bi phase islands 7 and the matrix 6 as shown in Fig. 2 wherein lubricant oil is retained in the recessions.

Further, in the case where there are present hard

20 intermetallic compound grains adjacent to the Pb and/or Bi phase islands in the sliding material, Pb and/or Bi, each having the low melting point is prevented from excessive flowing out by the existing intermetallic compounds whereby the anti-seizure property under high

25 temperature is improved. While there is a concern about that the soft Pb and/or Bi phase is liable to become a trigger point of fatigue rupture due to cyclic loading, even if cracks occurred from trigger points of

the Pb and/or Bi phase, they are prevented from extending to the matrix by hard intermetallic compounds whereby the copper alloy sliding material is improved in fatigue strength.

5 On the basis of the above consideration, according to a first aspect of the invention, there is provided a copper alloy sliding material comprising Pb and/or Bi in an amount or a total amount of 1 to 10 mass % and having not less than 100 of Vickers
10 hardness, wherein intermetallic compounds are present adjacently to the Pb-phase and/or the Bi phase, which has excellent foreign substance embeddability and excellent anti-adhesion property. The copper alloy sliding material have also excellent anti-seizure
15 property and improved wear resistance and fatigue resistance properties without increasing the amount of Pb and/or Bi. Further, since the sliding material has not less than 100 of Vickers hardness, it is improved in the load capacity and also the fatigue resistance
20 property under a high surface load.

 According to one feature of the invention, the copper alloy sliding material is a sintering alloy and comprises, by mass percent, 0.5% to 15% Sn, at least one of 0.5% to 10% Ni and 0.1% to 10% Ag in an
25 amount or a total amount of 0.1 % to 10%, at least one of Pb and Bi in an amount or a total amount of 1% to 10%, and the balance essentially of Cu. Thus, when sintering the copper alloy sliding material, Pb and/or

Bi melts under a high temperature atmosphere to produce a liquid phase of which catalyst effect promotes diffusion of components of the matrix around the liquid phase so as to produce an intermetallic compound at
5 interfaces among the matrix and Pb and/or Bi phase islands, so that there can be produced a metal structure having an intermetallic compound adjacent to the Pb-phase islands and/or the Bi-phase islands.

Here, a description of the alloying elements
10 of the sintering copper alloy will be provided with regard to reasons of those defined amounts and advantageous effects obtainable from the defined amounts.

(a) Sn (0.5 to 15 mass %):

15 Sn strengthens the alloy matrix thereby improving the fatigue resistance property of the alloy. It also reacts with Ni and Ag in the matrix around the soft Pb and/or Bi phase islands to produce an intermetallic compound. If the Sn amount is less than
20 0.5 mass %, the matrix strengthening effect thereof can not be obtained. If it exceeds 15 mass %, Cu-Sn system compounds are produced excessively, so that the alloy becomes brittle. Preferably, the Sn amount is 1 to 11 mass %.

25 (b) Ni and/or Sn (by mass, 0.5% to 10% Ni and/or 0.1% to 10% Ag in an amount or a total amount of 0.1% to 10%):

Ni and Ag produce intermetallic compounds, for example an Ni-Sn system or an Ag-Sn system,

respectively, to strengthen the alloy matrix thereby improving the fatigue resistance property of the alloy. However, less than 0.5 mass % Ni does not form the Ni-Sn system intermetallic compound, and less than 0.1 mass % Ag does not form the Ag-Sn system intermetallic compound. An excess amount of Ni and/or Ag exceeding 10 mass % in an amount or a total amount makes the matrix too brittle resulting in an unpreferable copper alloy sliding material.

10 (c) Pb and/or Bi (by mass, 1% to 10% in an amount or a total amount)

Pb and Bi form a liquid Pb-phase and a liquid Bi-phase during sintering, respectively, to promote the sintering reaction. The liquid Pb-phase and the liquid Bi-phase form soft phases dispersed in the matrix, respectively, to improve foreign substance embeddability and anti-seizure property of the alloy. If Pb and/or Bi is less than 1 mass % in an amount or a total amount, the above properties can not be obtained.

15 Bi-phase form soft phases dispersed in the matrix, respectively, to improve foreign substance embeddability and anti-seizure property of the alloy. If Pb and/or Bi is less than 1 mass % in an amount or a total amount, the above properties can not be obtained.

20 An exceeding 10 mass % amount thereof deteriorates strength including fatigue strength of the alloy.

According to another feature of the invention, the copper alloy sliding material further comprises, by mass percent, one or more of Fe, Al, Zn, Mn, Co and P (phosphorous) in an amount or a total amount of not more than 40%, whereby the matrix is strengthened to improve fatigue resistance of the alloy. However, an excess amount of one or more of

25 Mn, Co and P (phosphorous) in an amount or a total amount of not more than 40%, whereby the matrix is strengthened to improve fatigue resistance of the alloy. However, an excess amount of one or more of

them exceeding 40 mass % in an amount or a total amount makes the matrix too hard to deteriorate the conformability resulting in an unpreferable copper alloy sliding material.

5 According to a second aspect of the invention, there is provided a plain bearing comprising a back metal and the copper alloy sliding material being provided on the back metal. The plain bearing can be used for high speed and high power engines for
10 motor vehicles. When it is applied to such an engine, it exhibits good properties of anti-seizure, wear resistance and load carrying capacity under harsh operational conditions.

 According to one feature of the plain
15 bearing, an overlay layer of metal and/or resin is provided on the copper alloy sliding material. The plain bearing is excellent in initial conformability, foreign substance embeddability and anti-seizure property.

20

BRIEF DESCRIPTION OF THE DRAWINGS

 Fig. 1A is a schematic illustration of a microscopic photograph of a magnification of 200, which shows a metal structure of an embodiment sliding
25 material of the invention;

 Fig. 1B is a similar drawing to Fig. 1 but only differs therefrom in the point that the latter has a magnification of 2,000;

Fig. 2 is a drawing which illustrates a reason why the invention sliding material has improved anti-seizure property;

Fig. 3 is a cross-sectional view of an embodiment half shell bearing according to the invention;

Fig. 4 is a graph showing results of a seizure test; and

Fig. 5 is a graph showing results of a fatigue test.

Referring to the attached drawings, an embodiment of the invention, which is applied to an engine bearing for motor vehicles, will be described herein below.

15

BRIEF DESCRIPTION OF A PREFERRED EMBODIMENT OF THE PRESENT INVENTION

A half shell bearing 1 is shown Fig. 3, which is used as one pair of them. The bearing 1 comprises a back metal 2 which is made of a thin steel plate, for example, a copper alloy sliding material 4 which is provided on the back steel 2 via a bonding layer 3 of copper plating and an overlay layer 5 which is made of a soft metal or resin and provided on the copper alloy sliding material 4.

25

The copper alloy sliding material 4 is of a sintered alloy which consists of, by mass percent, 0.5% to 15% Sn, at least one of 0.5% to 10% Ni and 0.1% to

10% Ag in an amount or a total amount of 0.1% to 10%,
at least one of Pb and Bi in an amount or a total
amount of 1% to 10%, and the balance essentially of Cu.
It may further comprise, by mass percent, one or more
5 of Fe, Al, Zn, Mn, Co and P in an amount or a total
amount of not more than 40%. Preferably, the surface
hardness of the copper alloy sliding material 4 on the
back metal 2 has a micro-Vickers hardness of not less
than 100.

10 There is described, here, a method of
producing the half shell bearing 1.

 At first, an alloy powder having the above
chemical composition of the sintering alloy is prepared
from alloy components of Sn, one or more of Ni and Ag,
15 one or more of Pb and Bi, and Cu. The alloy powder may
comprise one or more of Fe, Al, Zn, Mn, Co and P.
Preferably, each particle of the alloy powder has a
particle size of not more than 250 μ m. The alloy
powder may be a pre-alloyed powder or a powder mixture
20 of alloy components.

 The alloy powder (i.e. the copper alloy
sliding material 4) is uniformly spread on a steel
plate of which surface is plated with copper (i.e. the
bonding layer 3). The steel plate with the alloy
25 powder is heated at a temperature of 800 to 920°C in a
reduction atmosphere for about 15 minutes for sintering
the alloy powder. The steel plate with a sintering
layer is subjected to rolling. Finally, the rolled

plate is again heated in order to further sinter the sintering layer, so that a bimetal plate is produced, in which a layer of the copper alloy sliding material 4 is provided on the steel plate.

5 During sintering in the process of producing the bimetal plate, Pb and/or Bi is melted to be a liquid phase and intermetallic compounds, such as an Ni-Sn system and an Ag-Sn system, produced adjacently to the Pb and/or Bi phase.

10 If a further amount of such intermetallic compounds is desired to provide at the interface between the Pb and/or Bi phase and the matrix, it is advisable to subject the bimetal plate to a heat treatment at 350 to 500°C for several hours after the
15 second sintering treatment. Thereafter, if the hardness of the sintering layer has not reached 100 of Vickers hardness, the bimetal is subjected to further rolling in order to obtain a Vickers hardness not less than 100 or improve the fatigue resistance of the
20 sintering layer by further strengthening.

 The thus produced bimetal plate is cut to a rectangular piece so as to have a predetermined width and a predetermined length. The sized bimetal plate is bent to a hemi-circular form and subsequently subjected
25 to finish machining of the surface of the sintering layer (i.e. the copper alloy sliding material 4). Thereafter, an overlay layer 5 is provided on the sintering layer, so that the half shell bearing 1 shown

in Fig. 3 is produced. Two of the half shell bearing 1 are associated with each other to a cylindrical form and used for engine bearings, for example, a main bearing receiving a crank shaft, a connecting rod bearing and so on.

It is noted that the above half shell bearing 1, as one example, comprised the back metal 2 with a thickness of 1.2 mm, the bonding layer 3 with a thickness of 5 μ m, the copper alloy sliding material 4 with a thickness of 0.3 mm and the overlay layer 5 with a thickness of 10 μ m.

The present inventors carried out tests of hardness, seizure and fatigue on invention examples and comparative examples of copper alloy sliding material of which chemical compositions are shown in Table 1 which includes also the result of the hardness test. The results of the seizure and fatigue tests are shown in Figs. 4 and 5, respectively. The hardness test was carried out with utilization of a Vickers hardness testing machine. The seizure test was carried out in the following manner:

1) a rotary shaft was supported by a specimen bearing which had substantially the same structure as that shown in Fig. 3 but lacking an overlay layer such as the overlay layer 5 in the drawing in order to clearly confirm the property of the copper alloy sliding material (corresponding to numeral 4 in Fig. 3), the rotary shaft being driven by an electric motor;

2) at first a running-in operation was conducted for 60 minutes;

3) after the running-in operation, the bearing load was increased step-by-step from a given initial bearing load in such a manner that 5 MPa was accumulated every 10 minutes; and

4) continuously rotating the rotary shaft and increasing the bearing load as stated above, a bearing load at a step just earlier than the relevant step of the bearing load, when the temperature of the bearing back surface exceeded 220°C or there occurred an abnormal driving current of the electric motor which drives the shaft, was determined as a maximum specific load without seizure.

Test conditions other than the seizure test are shown in Table 2.

The fatigue test was carried out on a small piece specimen only consisting of the copper alloy sliding material on which a testing load was exerted cyclically. The testing load was increased step-by-step from an initial load of 50 MPa in such a manner that 10 MPa was accumulated at every increase of load and the testing load was applied with sine-curvilinear 50,000 cycles at each loading step. A testing load, when there occurred a crack, was regarded as "the fatigue rapture load".

Table 1

	No.	COMPONENTS (mass %)						HARD- NESS* Hv.5
		Cu	Sn	Ni	Ag	Pb	Bi	
INVEN- TION EXAMPLE	1	Bal.	10	-	1	10	-	115
	2	Bal.	3	1	1	5	-	110
	3	Bal.	11	3	-	5	-	140
	4	Bal.	6	7	-	2	-	110
	5	Bal.	5	-	3	-	8	114
	6	Bal.	3	6	3	8	-	142
	7	Bal.	6	-	1	3	-	122
	8	Bal.	3.5	7	-	10	-	128
COMPARA- TIVE EXAMPLE	1	Bal.	3.5	-	-	23	-	87
	2	Bal.	10	-	1	10	-	82
	3	Bal.	3	1	1	5	-	73
	4	Bal.	11	-	-	5	-	135
	5	Bal.	5	-	3	-	12	107
	6	Bal.	6	-	1	-	-	123

*Note: The hardness is of Vickers.

Table 2

ITEM	CONDITION
SHAFT DIAMETER	53 mm
BEARING WIDTH	13 mm
PERIPHERAL SPEED OF SHAFT	10 m/minute
LUBRICANT OIL	SAE #20
OIL SUPPLY AMOUNT	12.5 ml/minute
MATERIAL OF SHAFT	JIS S55C as quenched
SHAFT SURFACE ROUGHNESS	Rmax: not more than 1.0 μ m

5 The following is an analysis of the test results.

Comparative Example No. 1 comprises a much amount of 23 mass % of Pb and corresponds to the conventional Kelmet bearing material. Invention
10 Example Nos. 1 to 8 have generally the same anti-

seizure property and significantly improved fatigue resistance property with relation to Comparative Example No. 1. This is because the metal structure of the Invention Examples is such that soft phase islands 5 7 of Pb and/or Bi are dispersed in the matrix 6 as shown in Fig. 1A and hard intermetallic grains 8 of an Ni-Sn system and/or an Ag-Sn system are present adjacently to the soft phase islands 7 as shown in Fig. 1B, the drawings are of schematic illustrations 10 produced from a microscopic observation.

Considering reasons why the copper alloy sliding material with a small amount of Pb could have excellent anti-seizure property, it is believed that, in the case of Example Nos. 1 to 8 wherein the hard 15 intermetallic compounds of an Ni-Sn system and/or an Ag-Sn system are present between the matrix and the phase islands of Pb and/or Bi, when the specimens receive a load or wear during sliding, the soft phase islands 7 of Pb and/or Bi and the matrix 6 at the 20 sliding-contact surface are recessed than the hard intermetallic compounds 8 to retain lubricant oil therein resulting in that the anti-seizure property is improved.

It is further believed that Example Nos. 1 to 25 8 were improved in the fatigue resistance property because they could have substantially the same anti-seizure property as Comparative Example No. 1 although the former comprised a smaller amount of Pb or Bi than

the latter, and that cracks occurred from trigger points of Pb or Bi phase islands are prevented from expanding to the matrix 6 resulting in improved fatigue strength because the harder intermetallic compounds of an Ni-Sn system and/or an Ag-Sn system than the matrix 6 are present close to the phase islands of Pb and/or Bi which are liable to be trigger points of occurrence of fatigue.

Here, a discussion is provided with regard to relationships among the anti-seizure and fatigue resistance properties and amounts of Ni, Ag and amounts of Pb, Bi.

First, Invention Example No. 3 and Comparative Example No. 4 have the same chemical composition of alloy components except for Ni. Invention Example No. 3, comprising Ni of the both elements of Ni and Ag each of which reacts with Sn to produce an intermetallic compound, is excellent in the anti-seizure and fatigue resistance properties than Comparative Example No. 4 comprising none of Ni and Ag. From this, it can be understood that an alloy component of Ni (or Ag) improves the anti-seizure and fatigue resistance properties of the copper alloy sliding material.

Next, Invention Example No. 7 and Comparative Example No. 6 have the same chemical composition of alloy components except for Pb. Invention Example No. 7, comprising Pb of the both elements of Pb and Bi, is

slightly inferior in the fatigue resistance property than Comparative Example No. 6 comprising none of Pb and Bi, because Pb is soft. However, a small amount of additive Pb (3 mass %) makes Invention Example No. 7
5 significantly excellent than Comparative Example No. 6 with regard to the anti-seizure property. Considering that Invention Example No. 7 comprises Ag, it is believed that the improvement of anti-seizure property is in virtue of a synergism of the Ag-Sn system
10 intermetallic compound and Pb.

Here, the amount of Bi (or Pb) will be discussed.

Invention Example No. 5 and Comparative Example No. 5 have the same chemical composition of
15 alloy components except for Bi. Comparative Example No. 5, comprising a much amount of Bi (12 mass %), has substantially the same anti-seizure property but is inferior in the fatigue resistance as compared with Invention Example No. 5. This is because, even if not
20 less than 10 mass % of Bi and/or Pb in total is added to the alloy material, an improvement of the anti-seizure property is not expectable and the fatigue resistance is merely deteriorated.

As stated above, while an excess amount of Pb
25 and/or Bi adversely affects the fatigue resistance of the copper alloy material, the proper amount thereof as defined in the present invention improves the anti-seizure and fatigue resistance properties.

Now, a discussion will be provided with regard to the hardness of the copper alloy sliding material 4.

Invention Example No. 1 and Comparative
5 Example No. 2, and Invention Example No. 2 and
Comparative Example No. 3 have the same chemical
composition, respectively. But, in the respective
combination, the both Examples are different in the
hardness from each other. Invention Example Nos. 1, 2
10 and Comparative Example Nos. 2, 3 have values of the
maximum specific load without seizure of which
differences are within a variance range of about 10
MPa. Thus, it can be said that they have generally the
same anti-seizure property. But, with regard to the
15 fatigue resistance, the hard Invention Example Nos. 1,
2 are significantly excellent than the soft Comparative
Example Nos. 2, 3. The copper alloy sliding material
is required to have not less than 100 of Vickers
hardness in order to have good fatigue resistance in
20 use under a high specific load.

As will be apparent from the above, according
to the invention copper alloy sliding material
comprising a smaller amount of Pb or an alternative of
Bi, excellent anti-seizure and fatigue resistance
25 properties can be obtained. The invention material
exhibits good properties of bearing for motor vehicle
engines which tend to have a high rotational speed and
a high power.

CLAIMS:

1. A copper alloy sliding material comprising Pb and/or Bi in an amount or a total amount of 1 to 10 mass % and having not less than 100 of Vickers hardness, wherein intermetallic compounds (8) are present adjacently to the Pb-phase and/or Bi-phase (7).
2. A copper alloy sliding material according to claim 1, which is a sintering alloy and comprises, by mass percent, 0.5% to 15% Sn, at least one of 0.5% to 10% Ni and 0.1% to 10% Ag in an amount or a total amount of 0.1% to 10%, at least one of Pb and Bi in an amount or a total amount of 1% to 10%, and the balance essentially of Cu.
3. A copper alloy sliding material according to claim 1 or 2, which further comprises, by mass percent, one or more of Fe, Al, Zn, Mn, Co and P (phosphorous) in an amount or a total amount of not more than 40%.
4. A plain bearing (1) comprising a back metal (2) and the copper alloy sliding material (4) being defined in any one of claims 1 to 3, wherein the copper alloy sliding material (4) is provided on the back metal (2).
5. A plain bearing according to claim 4, wherein an overlay layer (5) is provided on the copper alloy sliding material (4), the overlay layer (5) being one or more of metal and resin.

6. A copper alloy sliding material substantially as hereinbefore described with reference to and as shown in the accompanying drawings.
7. A plain bearing substantially as hereinbefore described with reference to and as shown in the accompanying drawings.
- 5



INVESTOR IN PEOPLE

Application No: GB 0030938.5
Claims searched: 1-7

20/

Examiner: Matthew Lawson
Date of search: 21 June 2001

Patents Act 1977
Search Report under Section 17

Databases searched:

UK Patent Office collections, including GB, EP, WO & US patent specifications, in:

UK Cl (Ed.S): F2A (AD38, AD44)

Int Cl (Ed.7): C22C; F16C 33/12

Other: Online: PAJ, WPI

Documents considered to be relevant:

Category	Identity of document and relevant passage		Relevant to claims
X,E	GB 2355016 A	(DAIDO) - pub. 11.04.01 - page 3 lines 4-11, page 5 line 22 - page 6 line 1, page 7 lines 12-18 and figures 1A, 2 & 4.	1-5
X	GB 2285266 A	(DAIDO) - the whole specification, especially page 4 lines 14-32, page 5 lines 26-30 and figure 1B.	1-5
X	GB 2312679 A	(TAIHO) - page 3 lines 5-17, page 4 lines 37-38, page 5 lines 4-8 & 22-29, page 6 lines 9-14 & page 6 line 38 - page 8 line 5.	1-5
X	GB 648379	(FEDERAL) - the whole specification, especially page 1 lines 78-87 and page 3 lines 77-81 & 110-111.	1-5
X	JP 070166278 A	(TOKAI) - WPI Abstract Accession No. 95-261641/34, PAJ Abv. 199509 and alloys in Tables 3, 4, 7 & 8.	1-5
X	JP 620067143 A	(KOMATSU) - PAJ Abv. 011267.	1,3-5
X	US 5282908	(NAKASHIMA) - the whole specification.	1,3-5

X	Document indicating lack of novelty or inventive step	A	Document indicating technological background and/or state of the art.
Y	Document indicating lack of inventive step if combined with one or more other documents of same category.	P	Document published on or after the declared priority date but before the filing date of this invention.
&	Member of the same patent family	E	Patent document published on or after, but with priority date earlier than, the filing date of this application.



Application No: GB 0030938.5
Claims searched: 1-7

21/

Examiner: Matthew Lawson
Date of search: 21 June 2001

Category	Identity of document and relevant passage		Relevant to claims
X	US 5303617	(ASADA) - column 2 lines 6-7, 13-17 & 20-21, column 3 lines 38-44, Examples 35-37, 51-55 & 57 of Table 2 and figure 1.	1-5
X	US 4608085	(EUDIER) - column 1 lines 5-7, column 2 lines 9-31 and column 4 lines 31-35.	1,3-5
X	US 4334926	(FUTAMURA) - the whole specification, especially column 2 lines 30-31, column 3 lines 7-16 and figure 1.	1,3-5

X	Document indicating lack of novelty or inventive step	A	Document indicating technological background and/or state of the art
Y	Document indicating lack of inventive step if combined with one or more other documents of same category.	P	Document published on or after the declared priority date but before the filing date of this invention.
&	Member of the same patent family	E	Patent document published on or after, but with priority date earlier than, the filing date of this application.